

THERMAL LABEL PAPER PRODUCT INFORMATION

150LH

FACESTOCK

ITEM	SPECIFICATION	TEST METHOD
Basis Weight	48.5# ± 4.9 (24 x 36 x 500 Sheets)	TAPPI T-410
	79 ± 8 g/m ²	
Caliper	3.2 Mils (81 ± 9µm)	TAPPI T-411
Image Color	Black	VISUAL CHECK
Image Density (ODU)	1.40 Minimum	Macbeth Densitometer
Background Density (ODU)	0.12 Maximum	Macbeth Densitometer
Tear Strength	MD 30 gf Minimum	TAPPI T-414
	CD 35 gf Minimum	
Tensile Strength	MD 5.5 kgf/15mm Minimum	TAPPI T-494
	CD 2.5 kgf/15mm Minimum	

PRESERVATION PROPERTIES

ITEM	SPECIFICATION	TEST METHOD
Plasticizer Resistance (Face)	Image 1.25 Minimum	40° C, Dry, 150 Hours
	Background 0.20 Maximum	
Water Resistance	Image 1.25 Minimum	Water Immersion, 24 Hours
	Background 0.20 Maximum	
Oil Resistance	Image 1.25 Minimum	40° C, Dry, 150 Hours
	Background 0.20 Maximum	
Moisture Resistance	Image 1.25 Minimum	40° C, 90% RH, 150 Hours
	Background 0.20 Maximum	
Heat Resistance	Image 1.25 Minimum	90° C, Dry, 24 Hours
	Background 0.20 Maximum	
Light Resistance	Image 1.25 Minimum	5000 lx, 100 Hours
	Background 0.10 Maximum	

*Remarks: Image and Background measured by Macbeth (ODU)

Scannable up to 660 nm

Specification may change without notice

150LH LAMINATED PRODUCT

GRADE	UNIT	G12
Application Temperature	°F	-40 to 122
	°C	-40 to 50
Service Temperature	°F	-65 to 131
	°C	-54 to 55
Basis Weight (24 x 36 x 500)	LBS	101 ± 11
	g/m ²	166 ± 18
Caliper	µm	161 ± 19

*Custom: Please contact the Sales/Marketing department for application specific adhesives.



Liner: 42# Super Calendered White Kraft

Caliper: 2.5 Mils ± 10% (64 ± 7µm)

Opacity: 65% Maximum (Photovolt)

STORAGE CONDITION

Below 95°F (35°C) and less than 85% RH in a warehouse avoiding direct sunlight.



Comments: Sensitivity curves are for general reference only.